




# MIPOLAM® TROPLAN PLUS ever





# MIPOLAM® TROPLAN PLUS










34-43



## MIPOLAM® TROPLAN PLUS ever Care



- 1 EVERCARE™ surface treatment
- (2) Compacted calendered homogeneous floorcovering
- ☐ High performance flexible homogeneous multipurpose flooring
- □ Available in sheet
- □ Directional design
- ☐ EVERCARE™ surface treatment: for ease of maintenance
- □ Densely compacted surface for improved wear maintenance
- ☐ Anti-bacterial and fungicidal
- ☐ Antistatic

Compacted sheet, without foam backing



EXCLUSIVE PATENTED TECHNOLOGY BY GERFLOR®

# THE BEST CHEMICAL STAIN RESISTANCE SURFACE TREATMENT Other non-treated floor covering Missing treatment and uneven thickness 100% non-porous surface Water-repellent effect Non-treated product







1060 Anthracite



1036 Medium Blue

# MIPOLAM® TROPLAN PLUS ever care



#### MIPOLAM® TROPLAN PLUS

SECO	DI	DI		N.E.
DESC	.KI	ווץ	W	N.

Total thickness	ISO 24346 (EN 428)	mm	2
Weight	ISO 23997 (EN 430)	g/m²	3100
Width / Length of sheet	ISO 24341 (EN 426)	cm / lm	200 / 20

#### CLASSIFICATION


Norm / Product specification			ISO 10581 (EN 649)
European classification	ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	KV	<2
Electrical resistance	EN 1081	0	10 <sup>9</sup> -10 <sup>10</sup>
Slip resistance dry	EN 13893		≥0.3
Slip resistance wet	DIN 51130	class	R9

Slip resistance wet	DIN 51130	class	R9
PERFORMANCES			
Wear resistance	EN 660.2	mm³	≤ 2.0
Wear group	EN 649	group	T
Type binder content	ISO 10581	type	***
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.4
Residual indentation	ISO 24343-1 (EN 433)	mm	≈0.03
Castor chair test	ISO 4918 (EN 425)	-	OK
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.K)	≈0.25
Colour fastness	ISO 105 - B02	degree	≥ 6
Chemical products resistance	ISO 26987 (EN 423)		OK
Anti-bacterial and fungicidal treatment	<u>-</u>	-	OK
Surface treatment			EVERCARE™
Color number	-	Co	18
ENVIRONMENT / INDOOR AIR QUALITY		73.	
TVOC after 28 days	ISO 16000 - 6	μg/m³	<10
Certification		-	Floorscore®
CE MARKING	MN.		, r
	N		<b>7 8 2</b>
CE	EN 14041		OK  ≈0.25  ≥ 6  OK  OK  EVERCARE™  18  <10  Floorscore®

#### **ENVIRONMENT / INDOOR AIR QUALITY**

TVOC after 28 days	ISO 16000 - 6	μg/m³	<10	
Certification	7	-	Floorscore®	

#### **CE MARKING**



MIPOLAM® TROPLAN PLUS is a flexible homogeneous calendered compacted floorcovering in sheet, with directional design color dyed as a raw mixture to ensure color throughout the thickness. Its surface is densely compacted for improved wear and ease of maintenance.

It benefits from Evercare™ which has the highest chemicals resistance on the market for durable appearance and cleanliness of the product. It is probably the best treatment against chemicals ever on homogeneous flooring. No wax for life!

MIPOLAM® TROPLAN PLUS features bacteriostatic and fungistatic treatment. The flooring complies with the EN 649 (34-43) and has a Group T wear rating. It is suitable for heavy traffic areas.



#### MIPOLAM® TROPLAN PLUS, LESS SPEAKING FOR MORE ACTIONS



COMPOSITION FREE of formaldehyde FREE of heavy metals FREE of solvent



CONTENT 25% average recycled content 100% REACH compliant recycled content



**PECYCLARILITY** 100% recyclable product



INDOOR AIR QUALITY TVOC emissions between 10 and 100 firmes better than norms requirements Floorscore certified No formaldehyde emission



INSTALLATION free installation systems



& Profiles

WELLNESS Health: Antibacterial activity (inhibits growth > 99%)

บริษัท ไทยวัฒนาสามัคคี จำกัด Showroom: Monday - Saturday 8am - 5pm

www.twsplus.com E-mail: sale.twsplus@gmail.com Line Official : @twsplus





# MIPOLAM® TROPLAN PLUS ever (co

#### Performances and benefits



Excellent abrasion resistance



Available in 2 m sheet



Flexible flooring, easy to install & weld



Matt finish surface: enhanced design & colour



Homogeneous vinyl flooring suitable for medium to heavy duty traffic areas



Directional design available in 18 references

### FEWER VOC'S, BETTER INDOOR AIR QUALITY



#### COMPOSITION 100% REACH compliant

- FREE of formaldehyde
- FREE of heavy metals
- FREE of solvent



#### WELLNESS

#### Health

 Antibacterial activity (inhibits growth > 99 %)





- TVOC emissions 100 times lower than norm requirements (TVOC <10 µg/m³ after 28 days)
- Floorscore certified
- M1 certified
- Comply with AgBB protocol
- No formaldehyde emission



#### RECYCLABILITY

100 % recyclable product



#### RECYCLED CONTENT

• 100 % REACH compliant recycled content

#### INSTALLATION

installation should be carried out in accordance with local standards. Subfloor should be smooth, hard, clean and dry prior to laying. Where applicable, the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatize 24 hours before installation in a room temperature of between 18-24°C. All seams must be hot welded using Gerflor® matching welding rod.

#### **MAINTENANCE**

No emulsion dressing is required. Maintenance should be carried out regularly to retain in the appearance and durability of the floor. The floorcovering should be maintained with regular sweeping and damp mopping using a neutral cleanser. More intense cleaning should be carried out using a fine spray cleaning pad under a floor machine, or for larger areas combined machine cleaning.

🗥 Rubber leaves indelible stains on vinyl flooring: do not use mats with rubber backing and replace tubular furniture feet with those made of PVC or polyamide.